

| | |
|----------------------------|---|
| Article No. | 2180 |
| EAN-Code | 4251744521801 |
| Title | Oak Live Edge Top Rustic 40x2000x1000 Epoxy black |
| Thickness in mm | 40 |
| Length in mm | 2000 |
| Width in mm | 1000 |
| Type of wood | Wildeiche Tischplatte Baumkante geölt |
| Quality | Asteiche Epoxid schw |
| Type of lamella | DL Baumkante geölt |
| Width of lamella | fallend mit Baumkante |
| Packaging / Foiling | foliert+Karton |
| Description | Solid wood panel for table top, Europ. Oak, nature "Live Edge", 1-layer, Quality RUSTIC (topside Rustic, not color sorted, sap only on bottom side, topside knots and cracks filled with black epoxy), EGP long lamella, random widths of lamella, m.c. 8+/-2%, glued D4-EN 204, sanded 120 grit, all sides oiled, single foiled+cardbox, size 40x2000x1000mm |
| Wood moisture | At the end of production, the wood moisture is approx. 8 +/- 2%, which corresponds to the equilibrium moisture when used in closed rooms with a healthy living climate of 20°C / 55% humidity |
| Gluing | All solid wood panels / glued wood panels are glued formaldehyde-free using tested German brand glues (e.g. Jowatt, Kleiberit) of stress classes D3 and D4 in accordance with DIN/EN 204. Areas of application for these PVAc glues (=white glues) are indoor areas with frequent short-term exposure to runoff water or condensation and/or exposure to high humidity. As well as outdoor areas, but protected from the weather. The glue content for solid wood panels is only approx. 0.1%. The PVA glues used do not release any formaldehyde (in contrast, chipboards are usually bound to formaldehyde resin and have a glue content of up to 10%). With D3 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/1 (dry area according to EN 13986) can be achieved. With D4 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/2 (wet area according to EN 13986) can be achieved. |
| DIN standard | All LARBON® solid wood panels clearly exceed the necessary specifications of the European standards DIN EN 13353 (technical requirements) and DIN EN 13017-2 (optical appearance classes). |