

<b>Article No.</b>	2183
<b>EAN-Code</b>	4251744521832
<b>Title</b>	Oak Live Edge table EGP 2-layer 40x2000x1000 oiled
<b>Thickness in mm</b>	40
<b>Length in mm</b>	2000
<b>Width in mm</b>	1000
<b>Type of wood</b>	Wildeiche Tischplatte 2-S Baumkante
<b>Quality</b>	Asteiche Epoxid tran
<b>Type of lamella</b>	DL 20+20mm Baumkante
<b>Width of lamella</b>	fallend mit Baumkante
<b>Packaging / Foiling</b>	foliert+Karton
<b>Description</b>	Solid wood panel for table top, Europ. Oak, nature "Live Edge", 2-layer, Quality RUSTIC (topside Rustik, no sap / sap only on bottom side C, topside knots filled black), EGP long lamella, random widths of lamella, m.c. 8+/-2%, glued D4-EN 204, sanded 100 grit, wax oiled, 3-metal stringer, single foiled, packed in cardboiard, size 40 (20+20)x2000x1000mm
<b>Wood moisture</b>	At the end of production, the wood moisture is approx. 8 +/- 2%, which corresponds to the equilibrium moisture when used in closed rooms with a healthy living climate of 20°C / 55% humidity
<b>Gluing</b>	All solid wood panels / glued wood panels are glued formaldehyde-free using tested German brand glues (e.g. Jowatt, Kleiberit) of stress classes D3 and D4 in accordance with DIN/EN 204. Areas of application for these PVAc glues (=white glues) are indoor areas with frequent short-term exposure to runoff water or condensation and/or exposure to high humidity. As well as outdoor areas, but protected from the weather. The glue content for solid wood panels is only approx. 0.1%. The PVA glues used do not release any formaldehyde (in contrast, chipboards are usually bound to formaldehyde resin and have a glue content of up to 10%). With D3 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/1 (dry area according to EN 13986) can be achieved. With D4 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/2 (wet area according to EN 13986) can be achieved.
<b>DIN standard</b>	All LARBON® solid wood panels clearly exceed the necessary specifications of the European standards DIN EN 13353 (technical requirements) and DIN EN 13017-2 (optical appearance classes).